



**Notes:**

1. Asphalt shall be cut with a core drill
2. Potholing shall be performed with a dry / forced air vac machine
3. Pothole backfill shall be control density fill
4. Pothole shall be finished with 3" asphalt concrete CL B compacted depth
5. Pothole edge shall be cleaned and tacked with sealer CSS1 and sealed with hot mix asphalt cement AR4000W

Approved:  March 16, 2018

City Engineer Date

**STREET STANDARD DETAIL**



Dwg No: **S27**

**POTHOLE RESTORATION**