



Notes:

1. Asphalt shall be cut with a core drill
2. Potholing shall be performed with a dry / forced air vac machine
3. Pothole backfill shall be control density fill
4. Pothole shall be finished with 3" asphalt concrete CL B compacted depth
5. Pothole edge shall be cleaned and tacked with sealer CSS1 and sealed with hot mix asphalt cement AR4000W

Approved:  January 27, 2010  
 City Engineer Date



Dwg No: **S29**  
**POTHOLE RESTORATION**

**STREET STANDARD DETAIL**